

### Surface Energy Data for Nafion, CAS #31175-20-9

Source <sup>(a)</sup>	Mst. Type <sup>(b)</sup>	Data <sup>(c)</sup>	Comments <sup>(d)</sup>
Curtin, 2004 <a href="#">(278)</a>	Contact angle	$\theta_{\text{W}}^{\text{A}} = 95^{\circ}; 23^{\circ}\text{C}, 50\% \text{RH}$	Extruded NR112.
Curtin, 2004 <a href="#">(278)</a>	Contact angle	$\theta_{\text{W}}^{\text{A}} = 94^{\circ}; 23^{\circ}\text{C}, 50\% \text{RH}$	Cast NR112.
Curtin, 2004 <a href="#">(278)</a>	Contact angle	$\theta_{\text{W}}^{\text{A}} = 85^{\circ}; 23^{\circ}\text{C}, 50\% \text{RH}$	Extruded NR112, boiled before testing.
Curtin, 2004 <a href="#">(278)</a>	Contact angle	$\theta_{\text{W}}^{\text{A}} = 88^{\circ}; 23^{\circ}\text{C}, 50\% \text{RH}$	Cast NR112, boiled before testing.

©2009 Diversified Enterprises